

Exhibit B

**JV "NALVES"**

Home · Prices · Counter Shapess

C1 Z1Ru En

**SHORT TECHNICAL CHARACTERISTICS  
OF ~~REGENERATED LEATHER~~ PASTEBOARD GRADE  
S1 (SO).**

BEST AVAILABLE COPY

Regenerated leather is delivered in folio measuring 1,0×1,5 m and thickness is ranged from 1,0 to 4,0 mm.

Our regenerated leather has dense structure and at the same time light specific gravity, which makes footwear extremely light and comfortable.

**Approximate physico-mathematical characteristics.**

- Specific Gravity (g/cm<sup>3</sup>) ..... 0,80
- Tensile Strength in dry condition (kg/cm<sup>2</sup>):
  - Extensibility ..... 65
  - Expansibility ..... 60
- Tensile strength in wet condition (kg/cm<sup>2</sup>):
  - Transversal..... 30
- Tensility (%):
  - Longitudina ..... 20-25
  - Transversal ..... 25-30
- Moistening or drying (linear dimensions changes), (%):
  - Longitudina..... 2,0
  - Transversa..... 2,5
- Moistening or drying in two hours, (%): .... about 30-35

Copyright © 2000 JV "NALVES"

Home · Prices · Counter Shapess